

APPLICATION DATA - PLASTICS

COMPUTRAC® MAX® 2000XL

RESIN	MAX-2000XL	STATISTICS	KARL FISCHER
ABS	0.040% 0.002 6-8 minutes	Mean Standard Deviation Test Time	0.042% 0.002
Acrylic	0.085% 0.007 7-9 minutes	Mean Standard Deviation Test Time	0.084% 0.002
Nylon 66	0.062% 0.002 7-9 minutes	Mean Standard Deviation Test Time	0.063% 0.005
Nylon 6	0.077% 0.005 8-10 minutes	Mean Standard Deviation Test Time	0.077% 0.002
Polyester	0.007% 0.000 4-5 minutes	Mean Standard Deviation Test Time	0.007% 0.0003
Polycarbonate	0.025% 0.002 5-7 minutes	Mean Standard Deviation Test Time	0.024% 0.003
PBT	0.010% 0.003 3-5 minutes	Mean Standard Deviation Test Time	0.010% 0.002
Polyethylene	0.003% 0.000 8-10 minutes	Mean Standard Deviation Test Time	0.002% 0.0004
Polypropylene	0.005% 0.001 4-5 minutes	Mean Standard Deviation Test Time	0.005% 0.0002
Polyurethane	0.033% 0.002 5-7 minutes	Mean Standard Deviation Test Time	0.033% 0.001



ARIZONA INSTRUMENT LLC

3375 N. Delaware Street, Chandler, AZ 85225 • (602) 470-1414 • (800) 528-7411 • www.azic.com

Exclusive Manufacturer of Computrac® Moisture Analyzers and Jerome® Toxic Gas Analyzers

PVC	0.017% 0.004 5-7 minutes	Mean Standard Deviation Test Time	0.018% 0.001
TPO	0.078% 0.006 7-9 minutes	Mean Standard Deviation Test Time	0.078% 0.004
PC/ABS Blend	0.014% 0.003 5-6 minutes	Mean Standard Deviation Test Time	0.013% 0.0010
PET/PC Blend	0.014% 0.002 4-5 minutes	Mean Standard Deviation Test Time	0.014% 0.001
PC/PBT Blend	0.045% 0.003 6-7 minutes	Mean Standard Deviation Test Time	0.041% 0.001



ARIZONA INSTRUMENT LLC

3375 N. Delaware Street, Chandler, AZ 85225 • (602) 470-1414 • (800) 528-7411 • www.azic.com

Exclusive Manufacturer of Computrac® Moisture Analyzers and Jerome® Toxic Gas Analyzers